

[close window](#)[Print](#)**Submitted Abstract**

on November 02, 11:58 PM

for MRS Spring 2005

Abstract Proof**CONTROL ID:** 128333**CONTACT (NAME ONLY):** Shigeo Maruyama**Abstract Details****PRESENTATION TYPE:** Invited Speaker**SYMPOSIUM:** U: Science and Applications of Carbon Nanotubes**KEYWORDS:** Single-Walled Carbon Nanotubes, Vertically Aligned, CVD Growth.**Abstract****TITLE:**

ACCVD Growth of Vertically Aligned Single-Walled Carbon Nanotubes on a Quartz Substrate

AUTHORS (ALL): [Maruyama, Shigeo](#)¹.**INSTITUTIONS (ALL):** 1. Dept. of Mech. Eng., The University of Tokyo, Tokyo, Japan.**ABSTRACT BODY:**

Vertically aligned single-walled carbon nanotubes (SWNTs) up to 5 microns thick were produced by an alcohol CVD process [1]. In contrast to the first report of CVD growth of vertically aligned SWNTs [2], hydrogen gas was supplied only during the heating-up stage with the improved background vacuum condition. A time-progressive investigation of the growth process was studied by observing SEM images of SWNT films grown for different CVD times. Measurements of the film thickness by both SEM and optical absorbance show a non-linear growth rate, as well as an eventual decrease in the film thickness after extended reaction times. This is attributed to the presence of oxygen in the reaction chamber, which decreases catalyst activity as well as oxidizes the nanotube film. By using the relation between light absorbance and the thickness determined by SEM, the in situ monitoring of the vertically aligned SWNT film thickness has made possible for the further investigation of the growth mechanism.

Polarization dependence of resonant Raman scatterings from vertically aligned SWNT films and polarized optical absorption properties of SWNTs are studied by using these samples.

References

[1] S. Maruyama, R. Kojima, Y. Miyauchi, S. Chiashi and M. Kohno, "Low-Temperature Synthesis of High-Purity Single-Walled Carbon Nanotubes from Alcohol," Chem. Phys. Lett., (2002), vol. 360, no. 3-4, pp. 229-234.

[2] Y. Murakami, S. Chiashi, Y. Miyauchi, M. Hu, M. Ogura, T. Okubo, S. Maruyama, "Growth of vertically aligned single-walled carbon nanotube films on quartz substrates and their optical anisotropy," Chem. Phys. Lett., (2004), vol. 385, no. 3-4, pp. 298-303.

[3] Y. Murakami, S. Chiashi, E. Einarsson and S. Maruyama, "Polarization dependence of resonant Raman scatterings from vertically aligned SWNT films," submitted to Phys. Rev. B.

[4] Y. Murakami, E. Einarsson, T. Edamura and S. Maruyama, "Polarized Optical Absorption Properties of Single-Walled Carbon Nanotubes," submitted to Phys. Rev. Lett.

(No Table Selected)

Abstract Central™ (patent pending). © [ScholarOne](#), Inc., 2004. All Rights Reserved.
Abstract Central is a trademark of ScholarOne, Inc. ScholarOne is a registered trademark of ScholarOne, Inc.
[Terms and Conditions of Use](#)