

Abstract for an Invited Paper
for the MAR08 Meeting of
The American Physical Society

Cross-polarized optical absorption of single-walled carbon nanotubes probed by photoluminescence excitation spectroscopy, UV-Vis-IR and polarized Raman Scatterings
SHIGEO MARUYAMA, The University of Tokyo

Because of the depolarization effect, or so-called antenna effect, optical absorption of single-walled carbon nanotubes (SWNTs) is weak when excited by light polarized perpendicular to the nanotube axis. However, in photoluminescence (PL) excitation spectra of isolated SWNTs, PL peaks due to cross-polarized excitation can be clearly identified. By decomposing the cross-polarized component, the optical transition energy of E12 or E21 can be measured, and the smaller exciton binding energy for perpendicular excitations is concluded [1]. Cross-polarized absorption is dominant in the absorption of a vertically aligned film of SWNTs [2] when excited from the top of the film. In our previous study, a pi-plasmon absorption at 5.25 eV was revealed in contrast to 4.5 eV for parallel excitation [3]. Resonant Raman scattering from such a film is also influenced by the cross-polarized excitation [4]. Even though a Kataura plot for the E33 and E44 range has been proposed by using such a vertically aligned film [5], polarized Raman scattering spectra reveal more complicated features in the system because of the small bundle size, typically 5-8 nanotubes [6].

References:

- [1] Y. Miyauchi, M. Oba, S. Maruyama, Phys. Rev. B 74 (2006) 205440.
- [2] Y. Murakami, S. Chiashi, Y. Miyauchi, M. Hu, M. Ogura, T. Okubo, S. Maruyama, Chem. Phys. Lett. 385 (2004) 298.
- [3] Y. Murakami, E. Einarsson, T. Edamura, S. Maruyama, Phys. Rev. Lett. 94 (2005) 087402.
- [4] Y. Murakami, S. Chiashi, E. Einarsson, S. Maruyama, Phys. Rev. B 71 (2005) 085403.
- [5] P. T. Araujo, S. K. Doorn, S. Kilina, S. Tretiak, E. Einarsson, S. Maruyama, H. Chacham, M. A. Pimenta, A. Jorio, Phys. Rev. Lett. 88 (2007) 067401.
- [6] E. Einarsson, H. Shiozawa, C. Kramberger, M. H. Ruemmel, A. Gruneis, T. Pichler, S. Maruyama, J. Phys. Chem. C (2007) published on Web.